

Nominal Composition

■ Material for electricity

[wt-%]

Alloys	C	Si	Mn	Ni	Cr	Al	Fe	
NCHW1	≤0.15	0.75~1.6	≤2.5	≥77	19~21		≤1	
NCHW2	≤0.15	0.75~1.6	≤1.5	≥57	15~18		BAL	
FCHW1	≤0.1	≤1.5	≤1.0		23~26	4~6	BAL	
FCHW2	≤0.1	≤1.5	≤1.0		17~21	2~4	BAL	
No30	≤0.1	≤1.5	≤1.0		23~26	4~6	BAL	
KANTHAL A-1					22	5.8	BAL	
KANTHAL AF					22	5.3	BAL	
KANTHAL D					22	4.8	BAL	
NIKROTHAL LX				75	20			
CN49W			0.5~2.5	42~48				Cu+Ni+Mn ≥99
CN30W			≤1.5	20~25				Cu+Ni+Mn ≥99
CN15W			≤1.5	8~12				Cu+Ni+Mn ≥99
CN10W			≤1.5	4~7				Cu+Ni+Mn ≥99
CN 5W			≤1.5	0.5~3				Cu+Ni+Mn ≥99
CM44W			10~13	1~4				Cu+Ni+Mn ≥98

■ Nickel and Nickel Alloy

[wt-%]

Alloys	C	Si	Mn	Ni+Co	Cu	Co	Fe	S	Si
NiW	≤0.15	≤0.3	≤0.3	≥99	≤0.2		≤0.4	≤0.01	≤0.30
Kovar	≤0.05	≤0.2	≤1.5	28~30		16~18	BAL		
Monel		≤0.5	≤2.0	63~70	BAL		≤2.5		
52%Nickel Iron	≤0.05	≤0.3	≤0.6	50.5			BAL		
42%Nickel Iron	≤0.05	≤0.3	≤0.6	41.0			BAL		
2%Mn-Ni	≤0.02	≤0.2	1.5~2.5	BAL	≤0.1		≤0.2		

■ Copper Alloy

[wt-%]

Alloys	Sn	P	Cu+Sn+P
PBW2 (C5191W)	5.5~7.0	0.03~0.35	≥99.5
PBW3 (C5212W)	7.0~9.0	0.03~0.35	≥99.5

■ Steel wire

[wt-%]

Alloys	C	Ni	Cr	Mo	
SUS 304	≤0.08	8.0~10.5	18.0~20.0		
SUS 305J-1	≤0.08	11.0~13.5	16.5~19.0		
SUS 310S	≤0.08	19.0~22.0	24.0~26.0		
SUS 316L	≤0.03	12.0~15.0	16.0~18.0	2.0~3.0	