

温度特性

■温度による抵抗増加係数 [ニッケルクロム電熱線、鉄クロム抵抗線]

温度[°C]	20	100	200	300	400	500	600	700	800	900	1000	1100	1200	1300
NCHW1	1.000	1.009	1.024	1.039	1.056	1.070	1.068	1.062	1.060	1.063	1.070	1.080	1.093	
NCHW2	1.000	1.014	1.031	1.048	1.065	1.077	1.083	1.085	1.090	1.095	1.103			
FCHW1	1.000	1.005	1.009	1.013	1.018	1.021	1.027	1.037	1.043	1.047	1.048	1.049	1.049	1.049
FCHW2	1.000	1.005	1.014	1.025	1.038	1.054	1.074	1.086	1.095	1.102	1.107	1.110	1.112	
A-1	1.000	1.000	1.000	1.000	1.000	1.010	1.020	1.020	1.030	1.030	1.040	1.040	1.040	1.040

